

# Technical Datasheet

# ALTITUDE COLLECTION

Direct Pressure Laminate, Level of use according to EN 13329: class **23/33 – AC5**



Heavy domestic use



Heavy commercial use



## DIMENSION

dimension	thickness (d)	12 ± 0,50 mm · dmax - dmin 0,50 mm		
	length	2000 ± 0,60 mm		
	width (b)	242 ± 0,10 mm · bmax - bmin 0,20 mm		
profile	long side	twin clic	short side	1clic2go Pure
groove	long side		short side	

## TOLERANCE

squareness	EN 13329	0,20 mm
straightness	EN 13329	0,30 mm
flatness crosswise	EN 13329	concave: 0,15% · convex: 0,20%
flatness length	EN 13329	concave: 0,50% · convex: 1,00%
gaps between elements	EN 13329	average: 0,15 mm · max: 0,20 mm
height difference between elements	EN 13329	average: 0,10 mm · max: 0,15 mm
misalignment		± 2 mm

## TEST

abrasion resistance	EN 13329	AC5 ( 6000 rpm)	
impact resistance	EN 13329	small ball 15 N · big ball 1000 mm	
micro scratch resistance	EN 13329	MSR-B2	
stain resistance	group 1 & 2	EN 13329	grade 5
	group 3		grade 4
castor chair test	EN 13329	no change in appearance or damage, as defined per EN 425	
effect of a furniture leg	EN 13329	no damage shall be visible, when testet with foot type 0	
thickness swelling	EN 13329	15%	
static indentation	EN 13329	0,05 mm	
light fastness	EN 13329	grey scale 4 at blue wool grade 6	
dimensional variations after changes in relative humidity	EN 13329	lengthwise 0,9 mm · crosswise 0,9 mm	
locking strength	EN 13329	length 1 kN/m · width 2 kN/m	
surface soundness	EN 13329	1,25 N/mm <sup>2</sup>	

## ENVIRONMENT

emission of formaldehyde	EN 717-1	class E1
--------------------------	----------	----------

## PHYSICAL BEHAVIOR

fire behavior	EN 13501-1	Cfl s1
slide resistance	EN 13893	technical class DS
thermal resistance	EN 12667	0,101 (m <sup>2</sup> K)/W ± 15%
thermal conductivity	EN 12664	0,120 W/(m*K) ± 15%
antistatic behavior	EN 1815	body voltage 2kV